

HCS® 200 µm All Silica Step-Index Optical Fiber

P/N: CF01493-41



Overview

High OH concentration in these fibers results in efficient power transmission in the wavelength range from high UV through visible light. The all-silica base construction also creates a high damage threshold and high-performance optical properties.

High temperature environments require the use of PYROCOAT® polyimide coating.

Typical Applications

Illumination
Laser Surgery
Radiation Analysis
Sensors
UV Fluorescene
UV Spectroscopy



HCS® 200 µm All Silica Step-Index Optical Fiber

P/N: CF01493-41

Product Description	200 All Silica Step-Index
Physical Characteristics	
Core Diameter	200 ± 5 μm
Cladding Diameter	240 ± 5 μm
Coating Diameter	260 ± 5 μm
Buffer Diameter	375 ± 30 μm
Core/Clad Offset	≤ 7 µm
Crimp & Cleave Compatible	No
Cladding Material	HCS fluoroacrylate
Buffer Material	ETFE
Standard Buffer Color	Natural
Optical Characteristics	
Туре	Multimode Step-Index
Numerical Aperture	0.22
Attenuation @ 820 nm	≤ 10 dB/km
Water Content	High OH
Mechanical and Environmental	
Operating Temperature	-65 to +125 °C
Short-Term Bend Radius	≥ 9 mm
Long-Term Bend Radius	≥ 14 mm
Proof Test Level	≥ 200 kpsi (1.38 GPa)
Order by Part Number	CF01493-41
Product Description Code	HCG-M0200T

For additional information please contact your sales representative.

You can also visit our website at www.ofsoptics.com or call 1-888-fiberhelp (1-888-342-3743) USA or 1-770-798-5555 outside the USA.







OFS Marketing Communications

Date: 12/19

HCS and PYROCOAT are registered trademarks of OFS Fitel, LLC. OFS reserves the right to make changes to the prices and product(s) described in this document at any time without notice. This document is for informational purposes only and is not intended to modify or supplement any OFS warranties or specifications relating to any of its products or services.