

## HCS® 550 µm All Silica Step-Index Optical Fiber

P/N: CF01493-43



#### **Overview**

High OH concentration in these fibers results in efficient power transmission in the wavelength range from high UV through visible light. The all-silica base construction also creates a high damage threshold and high-performance optical properties.

High temperature environments require the use of PYROCOAT® polyimide coating.

## **Typical Applications**

Illumination
Laser Surgery
Radiation Analysis
Sensors
UV Fluorescene
UV Spectroscopy



# HCS® 550 µm All Silica Step-Index Optical Fiber

P/N: CF01493-43

| Product Specifications  |                           |
|---|---------------------------|
| Product Description   | 550 All Silica Step-Index |
| Physical Characteristics  |                           |
| Core Diameter   | 550 ± 12 μm               |
| Cladding Diameter   | 600 ± 10 μm               |
| Coating Diameter  | 630 ± 10 μm               |
| Buffer Diameter   | 750 ± 30 μm               |
| Core/Clad Offset  | ≤ 9 µm                    |
| Crimp & Cleave Compatible   | No                        |
| Cladding Material   | HCS fluoroacrylate        |
| Buffer Material   | ETFE                      |
| Standard Buffer Color   | Natural                   |
| Optical Characteristics   |                           |
| Туре  | Multimode Step-Index      |
| Numerical Aperture  | 0.22                      |
| Attenuation @ 820 nm  | ≤ 10 dB/km                |
| Water Content   | High OH                   |
| Mechanical and Environmental  |                           |
| Operating Temperature   | -65 to +125 °C            |
| Short-Term Bend Radius  | ≥ 58 mm                   |
| Long-Term Bend Radius   | ≥ 94 mm                   |
| Proof Test Level  | ≥ 100 kpsi (0.689 GPa)    |
| Order by Part Number  | CF01493-43                |
| Product Description Code  | HCG-M0550T                |
| <b>OPTIONS:</b> Buffer Color, Buffer Diameter, Buffer Material, Cabling, Clad Diameter, Core Diameter, Connectorization, Numerical Aperture, Metalization, Proof Test |                           |

### For additional information please contact your sales representative.

You can also visit our website at www.ofsoptics.com or call 1-888-fiberhelp (1-888-342-3743) USA or 1-770-798-5555 outside the USA.







**OFS Marketing Communications** 

Date: 12/19

HCS and PYROCOAT are registered trademarks of OFS Fitel, LLC. OFS reserves the right to make changes to the prices and product(s) described in this document at any time without notice. This document is for informational purposes only and is not intended to modify or supplement any OFS warranties or specifications relating to any of its products or services.