

HCS® 940 µm All Silica Step-Index Optical Fiber

P/N: CF01493-44



Overview

High OH concentration in these fibers results in efficient power transmission in the wavelength range from high UV through visible light. The all-silica base construction also creates a high damage threshold and high-performance optical properties.

High temperature environments require the use of PYROCOAT® polyimide coating.

Typical Applications

Illumination
Laser Surgery
Radiation Analysis
Sensors
UV Fluorescene
UV Spectroscopy



HCS® 940 µm All Silica Step-Index Optical Fiber

P/N: CF01493-44

940 All Silica Step-Index 940 ± 15 μm 1000 ± 15 μm 1035 ± 15 μm 1400 ± 50 μm ≤ 11 μm No HCS fluoroacrylate ETFE Natural
1000 ± 15 μm 1035 ± 15 μm 1400 ± 50 μm ≤ 11 μm No HCS fluoroacrylate ETFE
1000 ± 15 μm 1035 ± 15 μm 1400 ± 50 μm ≤ 11 μm No HCS fluoroacrylate ETFE
1035 ± 15 μm 1400 ± 50 μm ≤ 11 μm No HCS fluoroacrylate ETFE
1400 ± 50 μm ≤ 11 μm No HCS fluoroacrylate ETFE
≤ 11 µm No HCS fluoroacrylate ETFE
No HCS fluoroacrylate ETFE
HCS fluoroacrylate ETFE
ETFE
Natural
Multimode Step-Index
0.22
≤ 10 dB/km
High OH
-65 to +125 °C
≥ 73 mm
≥ 118 mm
≥ 75 kpsi (0.689 GPa)
CF01493-44
HCG-M0940T

For additional information please contact your sales representative.

You can also visit our website at www.ofsoptics.com or call 1-888-fiberhelp (1-888-342-3743) USA or 1-770-798-5555 outside the USA.







OFS Marketing Communications

Date: 12/19

HCS and PYROCOAT are registered trademarks of OFS Fitel, LLC. OFS reserves the right to make changes to the prices and product(s) described in this document at any time without notice. This document is for informational purposes only and is not intended to modify or supplement any OFS warranties or specifications relating to any of its products or services.